

RHINOFLOOR EVOLUTION

Datasheet

Classification	Norm	Tarkett Value	Requirement
Product type	EN ISO 10582	Heterogeneous poly(vinyl chloride) floor coverings (ISO 10582)	
Domestic classification	EN ISO 10874	23 Heavy	
Commercial classification	EN ISO 10874	33 Heavy	
Industrial classification	EN ISO 10874	42 General	
Characteristics	Norm	Tarkett Value	Requirement
Total thickness	EN ISO 24346	2.50 mm	
Wear layer thickness	EN ISO 24340	0.55 mm	
Total weight	EN ISO 23997	3850 g/m ²	
Binder content	EN ISO 10582	Type I	
Surface treatment		RHINOMATT®	
Installation method		Glue-Down	
Performance for CE Marking	Norm	Tarkett Value	Requirement
Declaration of Performance	EN 14041	0132-0084-DoP-2020-03	
Technical Performance	Norm	Tarkett Value	Requirement
Dimensional stability	EN ISO 23999	Average measured value : ≤ 0.10 %	
Curl resultant to heat	EN ISO 23999	≤ 2 mm	
Reaction to fire	EN 13501-1	Bfl-s1	
Residual indentation	EN ISO 24343-1	≤ 0.05 mm	
Furniture leg effect	EN ISO 16581	No damage	No damage
Castor chair effect	EN ISO 4918	No damage	No damage
Impact sound reduction - ΔLw	EN ISO 717-2	3 dB	
Drum sound class	NF S31-074	C	
Thermal resistance (m ² K/W)	EN ISO 10456	0,02 m ² •K/W	
Colour fastness to light	EN ISO 105-B02	≥ 6	≥ 6
Chemical resistance	EN ISO 26987	Yes	
Slip resistance	EN 13893	Class DS (μ ≥ 0.30)	μ ≥ 0,30
Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)	≤ 2 kV
Underfloor heating		Suitable (maximum 27°C)	
Sustainability, Environment & Indoor Air Quality	Norm	Tarkett Value	Requirement
TVOC emissions after 28 days	EN 16516	Gold (≤ 10 μg/m ³)	
ReStart® Ready		Yes	
Total recycled content		39.5 %	
Carbon Footprint (Cradle-to-Gate, EPD Modules A1-A3)		7.71 kg CO ₂ e /m ²	
Material Health Statement		Yes	
Phthalate free		Yes	



RHINOFLOOR
EVOLUTION 

SUPER-NATURAL BEAUTY

DIGITAL DESIGN FLOORS