



WOOD H180 CLASSIC-P

HYBRID ADHESIVE FOR WOOD FLOORING

TECHNICAL SHEET NO: TDS02134 07/11/2023

SMART ADVANTAGES

- Bonds both solid & engineered wood flooring
- Excellent early grab formulation
- Very low emissions

DESCRIPTION

Bostik WOOD H180 CLASSIC-P is a high performance, permanently elastic single component hybrid adhesive for surface bonding of solid wood types, wood block, wood mosaic panels and strip parquet flooring up to 180mm wide, and engineered wood flooring up to 300mm.

It can be used for bonding onto concrete, wood, metal decking, and anhydrite screed.

It is suitable for use with warm water underfloor heating systems, provided a surface temperature of +27°C is not exceeded.



TECHNICAL CHARACTERISTICS

Colour	Beige
Form	Medium viscosity paste
Specific gravity	1.4 to 1.6 approx.
Composition	Hybrid polymer based
Application temperature	+10°C to +27°C
Application consumption	TKB-B3 800 to 900g/m ² TKB-B11 1000 to 1200g/m ²
Open times	Up to 40 minutes (depending on ambient temperature and humidity)
Drying times	Foot traffic: approx. 24 hours Sanding and varnishing: approx. 48 hours (depending on ambient temperature and humidity)
VOC emissions	Very low emissions EC1

COVERAGE

- Up to 15m² per 14kg bucket
(depending on the trowel size and substrate absorbency)

APPLICATION

IMPORTANT: Before using Bostik WOOD H180 CLASSIC-P, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

All phases of the application should comply with the current editions of:

- BS 8102 Code of Practice for protection of structures against water from the ground.
- BS 8201 Code of Practice for installations of for flooring of timber, timber products and wood-based panel products.
- BS 8204 Code of Practice for Screeds, Bases and In Situ Floorings.

Ensure the correct PPE is worn during use.

PREPARATION

- Ensure the subfloor is clean, sound and dry (<75%RH), free from laitance, cracks, structural defects and contaminants that may prevent adhesion (dust, oil, grease, paint, plaster, polish, some curing compounds, surface hardeners, additives and adhesive residues must be completely removed), and conforms to BS 8204 Code of Practice.
- The subfloor should be tested in accordance with British Standards using a calibrated hygrometer.
- A reading of 75% RH or less confirms that the subfloor is satisfactorily dry. Where this has not been attained, it is necessary to apply a Bostik HYTEC moisture control barrier or surface DPM to suppress residual moisture. For further information, contact Technical Services.
- Ensure the timber is acclimatised in accordance with the manufacturer's instructions, in the environment in which it is to be laid.
- If any areas of the subfloor require localised repairs, use Bostik Rapid Repair Mortar.
- For subfloors that are not sufficiently smooth, or require height build up to receive the particular floor covering being bonded, an application of a suitable Bostik smoothing compound and primer system is recommended. Please consult Technical Services for advice on specific products and subfloors.
- Before applying adhesive, ensure the substrate is dry and dust free.

UNDERFLOOR HEATING

- Bostik WOOD H180 CLASSIC-P can be used on substrates containing warm water underfloor heating systems. The system must be switched off 48 hours prior to, during and for 48 hours post application. To prevent rapid dehydration, wait 48 hours after installation before gradually turning up underfloor heating.
- For radiant underfloor heating systems, please contact Technical Services.

APPLICATION

- Ensure full (100%) contact is achieved between wood and adhesive. Spread the adhesive with a sweeping motion at a 60° angle with a suitable notched trowel over the floor.
- Place the floorcovering into the adhesive while it is still wet. Only apply enough adhesive to work within 40 minutes.

- Press firmly into the adhesive to ensure full contact. Use heavy objects, if required, to hold the wood firmly in place during the curing time.
- The bonded wood should take foot traffic after 24 hours. Leave bonded wood 48 hours before sanding and varnishing.

CLEANING

- Clean tools and equipment with white spirit immediately after use.
- Remove excess adhesive immediately by scraping method, then cleaning with a cloth dampened with white spirit (always test for colourfastness on small trial area first). Cured adhesive can be peeled off the surface. Do not use water as a cleaning agent.

STORAGE

- Store and transport securely in an upright position. Ensure the lid is fully closed. Store for up to 12 months from date of manufacture in original, unopened packaging in cool, dry conditions within the temperature range +10°C to +25°C and out of direct sunlight. Protect from frost.

PRECAUTIONS IN USE

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik WOOD H180 CLASSIC-P, available at www.bostik.com/uk.

PACKAGING

Product codes	30616178	14kg bucket (2 x 7kg pouches)
----------------------	----------	-------------------------------

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company that may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability that cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use that is inappropriate or use that is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top left-hand corner on the front of this document.

Sales	Tel: 0844 371 1192	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	sds.box-eu@bostik.com

DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

Bostik Ltd
Common Road,
Stafford, ST16 3EH, UK
Phone: +44 (0)1785 272625
www.bostik.com/uk

BOSTIK HOTLINE

Smart help +44 (0)1785 272625



All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.