

Texstar

Datasheet

Classification	Norm	Tarkett Value	Requirement
Product type	EN ISO 26986	Expanded (cushioned) poly(vinyl chloride) floor covering	
Domestic classification	EN ISO 10874	23 Heavy	
Commercial classification	ISO 10874	32 General	
Binder content	ISO 11638	Type I	
Characteristics	Norm	Tarkett Value	Requirement
Total thickness	ISO 24346	2.80 mm	
Wear layer thickness	ISO 24340	0.35 mm	
Total weight	ISO 23997	1760 g/m ²	
Performance for CE Marking	Norm	Tarkett Value	Requirement
Declaration of Performance	EN 14041	0007-0016-DOP-2020-01	
Reaction to fire	EN 13501-1	Cfl-s1	
Slip resistance	EN 13893	Class DS ($\mu \geq 0.30$)	
Slip resistance	DIN 51130	R10	
Electrical Propensity	EN 1815	Antistatic (≤ 2 kV)	≤ 2 kV
Thermal resistance (m ² K/W)	ISO 10456	0,040 m ² ·K/W	
Formaldehyde emission	EN 717-1	E1	
Technical Performance	Norm	Tarkett Value	Requirement
Impact sound reduction - ΔL_w	EN ISO 717-2	19 dB	
Residual indentation	EN ISO 24343-1	≤ 0.20 mm	
Chemical resistance	ISO 26987	Not affected	
Underfloor heating		Suitable (maximum 27°C)	
Colour fastness to light	ISO 105-B02	≥ 6	
Castor chair effect	ISO 4918	No damage	
Dimensional stability	EN ISO 23999	≤ 0.20 %	
Sustainability, Environment & Indoor Air Quality	Norm	Tarkett Value	Requirement
Emissions label		A+	
Phthalate free		Yes	
TVOC emissions after 28 days	EN 16516	Gold	
BREEAM rating		A+	
Dimensions and designs			
Roll		Roll 2x25m Roll 3 x 25 m Roll 4 x 25 m	
Number of designs available		19	



The above information is subject to modification for the benefit of further improvement (25/10/2021). According to the European Regulation N°305/2011 for CE Marking, the Declarations of Performance are available on our website <https://www.tarkett.com> Tarkett's instructions regarding installation, cleaning and maintenance should be observed. Please contact Tarkett at the address shown for the instructions.