



HYTEC A370 RAPID

SINGLE PART SURFACE MEMBRANE FOR CEMENTITIOUS SUBFLOORS

TECHNICAL SHEET NO: TDS02177 08/05/2024

SMART ADVANTAGES

- No mixing – reseal and reuse
- No priming required
- Up to 95% RH

DESCRIPTION

Bostik HYTEC A370 RAPID is a ready for use, one part, water-based, surface applied damp proof membrane. It has been developed to suppress residual construction moisture in textured and absorbent cementitious subfloors, concrete and sand/cement screeds. It is not recommended for use on dense compacted or profiled floors, calcium sulphate screeds or subfloors without an intact base DPM.

A Two coat application must be applied to provide protection up to a maximum hygrometer reading of 95% RH.

Bostik HYTEC A370 RAPID can also be used on heated sand/cement screeds with a confirmed moisture level not exceeding 90% RH when tested in accordance with BS 8203. Underfloor heating must have been fully commissioned and cracks, damages etc. in the subfloor must be fully repaired.



TECHNICAL CHARACTERISTICS

Colour	Applied blue, dries black
Form	Low viscosity liquid
Specific gravity	1.24 approx.
Composition	Polymer emulsion blend
Application temperature	+10°C to +30°C
Drying times	First coat: 15 to 30 minutes approx. at +20°C Second coat: 1 hour approx. at +20°C (Depending on ambient temperature and humidity)

COVERAGE

- Always apply two coats
- Two coats will cover up to 40m² per 12kg.
(Depending on the smoothness and absorbency of the floor surface)

APPLICATION

IMPORTANT: Before using Bostik HYTEC A370 RAPID, refer to the relevant Health & Safety Data Sheet, available at www.bostik.com/uk.

All phases of the application should comply with the current editions of:

- BS 8102 Code of practice for protection of below ground structures against water ingress.
- BS 5325 Code of practice for installation of textile floor coverings.
- BS 8203 Code of practice for installation of resilient floor coverings.
- BS 8201 Code of practice for installation of flooring of wood and wood-based panels.

Ensure the correct PPE is worn during use.

PREPARATION

- Bostik HYTEC A370 RAPID relies on adhesion to a sound, strong substrate. Ensure the subfloor is clean, sound, free from laitance, cracks, structural defects and contaminants that may prevent adhesion (dust, grease, paint, plaster, polish and poorly bonded adhesive residues), and conforms to BS 8204 code of practice.
- Highly polished surfaces or surface hardeners may require shot blasting. Power floated concrete must be abraded or shot blasted to provide a key for adhesion.
- The minimum working application and substrate temperature is +10°C and rising.

UNDERFLOOR HEATING

- Underfloor heating must have been fully commissioned.
- Bostik HYTEC A370 RAPID can be used on cementitious substrates containing warm water underfloor heating systems. The system must be switched off 48 hours prior to, during and for 48 hours post application. To prevent rapid dehydration, wait 48 hours after installation before gradually turning up underfloor heating.

APPLICATION

- Swirl the bottle gently to mix contents before use. Avoid excessive shaking as this will incorporate air into the product. Bostik HYTEC A370 RAPID must be applied in two coats.
- First coat: Decant the liquid into a paint tray, or similar container. Pre-wet a roller with Bostik HYTEC A370 RAPID. Apply the first coat in one direction (e.g., north-south or east-west), ensuring that the material is worked well into the substrate. Allow to fully dry.
- Bostik HYTEC A370 RAPID is considered dry once the blue colour has disappeared and a glossy black film is achieved.
- Second coat: When the first coat is dry, approximately 15 to 30 minutes at +20°C, apply the second coat at right angles to the first coat.
- It is essential that a pinhole free coating is achieved, and the correct coverage rate has been attained. The coverage rate is dependent on subfloor moisture levels and whether the subfloor contains underfloor heating (see table below for coverage rates).

Moisture levels	Coverage (2 coats)
<90% RH unheated screed	40m ²
90% to 95% RH unheated screed	30m ²
<90% RH heated screed	30m ²

Coverage is quoted at the maximum coverage rate per 12kg unit at two coats. Two coats must always be applied, and each coat will require 6kg of material.

- Allow to dry to a tack free film. At +20°C, the drying time will be approximately 1 hour. Drying times are based on good ambient conditions of +20°C and 65% RH. Colder and/or more humid conditions will delay drying.
- Bostik HYTEC A370 RAPID must be kept free from foot traffic and contamination from dust and materials from other trades until the Bostik smoothing compound has been applied.
- Bostik HYTEC A370 RAPID is not suitable for use as a wear layer and must always be covered with a Bostik smoothing compound.
- Cover with a minimum 3mm and maximum 10mm thickness of a Bostik smoothing compound to provide an absorption medium for any subsequent adhesive. The smoothing compound must be applied within 24 hours. NOTE: Should this not be achieved, then a fresh application of Bostik HYTEC A370 RAPID should be applied.
- Allow the smoothing compound to dry and bond the floor covering with the recommended Bostik adhesive.

CLEANING

- Clean tools and equipment with warm water immediately after use. Dried and hardened material can only be removed mechanically, or with white spirit.

STORAGE

- Store and transport securely in an upright position. Ensure the cap is fully closed. Store for up to 12 months from date of manufacture in original, unopened packaging in cool, dry conditions within the temperature range +5°C to +40°C and out of direct sunlight. Protect from frost.

PRECAUTIONS IN USE

For any application not covered, please contact Technical Services on +44 (0)1785 272625 or visit www.bostik.com/uk for advice.

Recommendations and suggestions are for guidance only, since conditions of use are completely beyond our control.

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate Health and Safety Data sheet for Bostik HYTEC A370 RAPID, available at www.bostik.com/uk.

PACKAGING

Product codes	30620708	12kg polyjerry
---------------	----------	----------------

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company that may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability that cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use that is inappropriate or use that is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company.

Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDS, and if in any doubt, contact the Company, quoting the code number in the top left-hand corner on the front of this document.

Sales	Tel: 0844 371 1192	customer.service@bostik.com
Technical Advice	Tel: 0844 371 1197	technical.service@bostik.com
Safety Data Sheets	Tel: 01785 272625	sds.box-eu@bostik.com

DISCLAIMER

Bostik offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations.

The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. They represent typical results for the products and are based on Bostik's research only. Since the conditions and methods of use of the products are beyond our control, Bostik expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contain herein.

Bostik Ltd
Common Road,
Stafford, ST16 3EH, UK
Phone: +44 (0)1785 272625
www.bostik.com/uk

BOSTIK HOTLINE

Smart help +44 (0)1785 272625



All advice, recommendations, figures and safety regulations provided are based on careful investigations, as well as the current state of our experience and are without obligation. Although the documentation has been compiled with the greatest care, we do not accept any liability for inaccuracies, mistakes, typesetting or printing errors. We reserve the right to modify the respective product if we deem it necessary. Since the design, the quality of the substrate and the processing conditions are beyond our assessment, no liability can be accepted for work performed on the basis of this documentation. We therefore advise you to carry out practical tests on site yourself. Our general Terms and Conditions of Sale and Delivery apply to all our sales and deliveries.