










Technical Specification

	CONSTRUCTION		CLASSIC	ELITE
	MACHINE GAUGE		1/10th Gauge	1/10th Gauge
	PILE HEIGHT	ISO 1766	6.2 mm	7.4 mm
	TUFT DENSITY	ISO 1763	147,250 tufts/m ²	162,750 tufts/m ²
	PILE WEIGHT		1,153 gms/m ² 34 oz/yd ²	1,423 gms/m ² 42 oz/yd ²
	TOTAL CARPET WEIGHT	ISO 8543	2,088 gms/m ²	2,247 gms/m ²
CARPET THICKNESS	ISO 1765	8.9 mm	10 mm	
WIDTH		4 & 5 metre	4 & 5 metre	
	COMPOSITION			
	PILE CONTENT	ISO 1833	100% Excellon Polypropylene	100% Excellon Polypropylene
	PRIMARY BACKING		Woven Polypropylene	Woven Polypropylene
SECONDARY BACKING		Woven Secondary	Woven Secondary	
	PERFORMANCE			
	SUITABILITY	ISO 10361	Heavy Domestic	Extra Heavy Domestic / Medium Contract
	WIRA ABRASION TEST	PD 6527:Clause 17	Exceeds 16,700 Rubs	Exceeds 43,400 Rubs
	STATIC LOADING	ISO 3416	15.7% Thickness Loss after 24 hrs recovery	16% Thickness Loss after 24 hrs recovery
	DYNAMIC LOADING	ISO 2094	33.9% Thickness Loss after 1,000 impacts	28% Thickness Loss after 1,000 impacts
TUFT ANCHORAGE	ISO 4919	Above 1kg	Above 1kg	
	COLOUR FASTNESS			
	LIGHT FASTNESS	ISO 105-B02	5/6 on all colours	5/6 on all colours
	WET FASTNESS	ISO 105-E01	5 on all colours	5 on all colours
	SHAMPOO FASTNESS	ISO 18168	5 on all colours	5 on all colours
	THERMAL VALUE			
	TOG VALUE	ISO 5085-1	1.1 Tog	1.2 Tog
	THERMAL RESISTANCE		0.11 m ² k/w	0.12 m ² k/w
	FLAMMABILITY			
	CE MARK RATING		Efl	Efl
	METHENAMINE PILL TEST	ISO 6925	Pass	Pass
	CHEMICAL IMPACT			
	FORMALDEHYDE		E1	E1
	BIOLOGICAL ATTACK			
	MOTH / INSECT RESISTANT		Insect & rot proof	Insect & rot proof
	ANTI STATIC			
			-0.2kv (Requirement less than +2.0kv)	-0.3kv (Requirement less than +2.0kv)

General Information

INSTALLATION - In all contract locations an 'all-over' stick down method is recommended to BS 5325 (1983). If underlay is required it should be of a firm and unyielding type and where installed in larger contract areas the carpet should be power stretched. For quantity orders requiring colour matching, please state at time of ordering.

MAINTENANCE - To maintain your carpet's appearance it is recommended that it is vacuumed at least three times per week, to remove particles of dirt and dust. An upright vacuum with beater bar and brush is recommended for use with cut pile carpets. Please note, over time, regular foot traffic will flatten the pile surface in the main walkways, causing areas of differential wear.

These areas will appear lighter or shaded in comparison to the less frequently used parts. This shading / tracking or flattening happens to all carpets with a pile surface and as such is not accepted as the basis for any complaint. Similarly Pile Reversal (or watermarking) is a phenomenon that can affect all cut pile carpets and as such is not accepted as a manufacturing fault.

MATCHING - This sample may not be from the same production batch as current stock and therefore should be used as a guide and not as an exact match. Equally matching between 5 metre and 4 metre widths cannot be guaranteed.

IMPORTANT - Minimum order length is 1.5 metres.

Greenwood & Coope Ltd

Brookhouse Mill, Greenmount, Bury, Greater Manchester, BL8 4HR
T: 01204 881234 | info@cormarcarpets.co.uk

www.cormarcarpets.co.uk

September 2023